



(11) **EP 0 940 797 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 158(3) EPC

(43) Date of publication:
08.09.1999 Bulletin 1999/36

(51) Int. Cl.⁶: **G09F 9/30**, H01L 33/00,
H05B 33/22

(21) Application number: **98938919.2**

(86) International application number:
PCT/JP98/03699

(22) Date of filing: **20.08.1998**

(87) International publication number:
WO 99/10862 (04.03.1999 Gazette 1999/09)

(84) Designated Contracting States:
DE FR GB NL

(30) Priority: **21.08.1997 JP 22543497**

(71) Applicant:
SEIKO EPSON CORPORATION
Shinjuku-ku, Tokyo 163-0811 (JP)

(72) Inventor: **YUDASAKA, Ichio**
Suwa-shi Nagano-ken 392-8502 (JP)

(74) Representative:
Sturt, Clifford Mark et al
Miller Sturt Kenyon
9 John Street
London WC1N 2ES (GB)


(54) **ACTIVE MATRIX DISPLAY**

(57) In order to provide an active matrix display device in which a thick insulating film is preferably formed around an organic semiconductive film of a thin film luminescent device without damaging the thin film luminescent device, the active matrix display device (1) is provided with a bank layer (bank) along a data line (sig) and a scanning line (gate) to suppress formation of parasitic capacitance in the data line (sig), in which the bank layer (bank) surrounds a region for forming the

organic semiconductive film (43) of the thin film luminescent device (40) by an ink-jet process. The bank layer (bank) consists of a lower insulating layer (61) composed of a thick organic material and an upper insulating layer (62) of an organic material which is deposited on the lower insulating layer (61) and has a smaller thickness so as to avoid contact of the organic semiconductive film (43) with the upper insulating layer (62).

Fig. 3

(B)



EP 0 940 797 A1

Description

Technical Field

[0001] The present invention relates to active matrix display devices which control thin film luminescent devices, such as electroluminescent (EL) devices emitting light by a driving current flowing in an organic semiconductive film, and light-emitting diode (LED) devices using thin film transistors (hereinafter referred to as TFTs).

Background Art

[0002] Active matrix display devices using current-control-type luminescent devices, such as EL devices or LED devices have been proposed. Since luminescent devices used in such types of display devices have self-luminescent functions; these have advantages, such as no installation of a backlight being necessary, whereas backlights are essential for liquid crystal display devices, and a wider viewing angle.

[0003] Fig. 22 is a block diagram of an active matrix display device using charge-injection-type organic EL devices. In the active matrix display device 1A shown in the drawing, a plurality of scanning lines **gate**, a plurality of data lines **sig** extending in the direction perpendicular to the direction of the scanning lines **gate**, a plurality of common feed lines **com** along the data lines **sig**, and a plurality of pixels 7 in a matrix formed by the data lines **sig** and the scanning lines **gate** are formed on a transparent substrate 10. A data line driving circuit 3 and a scanning line driving circuit 4 are provided for the data lines **sig** and the scanning lines **gate**, respectively. Each pixel 7 is provided with a conduction control circuit 50 for supplying scanning signals from a scanning line **gate**, and a thin film luminescent device 40 emitting light based on image signals supplied from a data line **sig** through the conduction control circuit 50. In this example, the conduction control circuit 50 has a first TFT 20 for supplying scanning signals from the scanning line **gate** to a gate electrode; a holding capacitor **cap** for holding image signals supplied from the data line **sig** through the first TFT 20; and a second TFT 30 for supplying the image signals held in the holding capacitor **cap** to the gate electrode. The second TFT 30 and the thin film luminescent device 40 are connected in series between an opposite electrode **op** (described below) and a common feed line **com**. The thin film luminescent device 40 emits light by a driving current from the common feed line **com** when the second TFT 30 is an ON mode, and this emitting mode is maintained by a holding capacitor **cap** for a predetermined time.

[0004] In such a configuration of active matrix display device 1A, as shown in Figs. 23, 24(A), and 24(B), the first TFT 20 and the second TFT 30 are formed of islands of a semiconductive film in each pixel 7. The first TFT 20 is provided with a gate electrode 21 as a part of

a scanning line **gate**. In the first TFT 20, one source-drain region is electrically connected to a data line **sig** through a contact hole in a first insulating interlayer 51, and the other region is connected to a drain electrode 22. The drain electrode 22 extends towards the region of the second TFT 30, and this extension is electrically connected to a gate electrode 31 of the second TFT 30 through a contact hole in the first insulating interlayer 51. One source-drain region of the second TFT 30 is electrically connected to a relay electrode 35 through a contact hole of the first insulating interlayer 51, and the relay electrode 35 is electrically connected to a pixel electrode 41 of the thin film luminescent device 40 through a contact hole in a second insulating interlayer 52.

[0005] Each pixel electrode 41 is independently formed in each pixel 7, as shown in Figs. 23, 24(B), and 24(C). An organic semiconductive film 43 and an opposite electrode **op** are formed above the pixel electrode 41 in that order. Although the organic semiconductive film 43 is formed in each pixel 7, a stripe film may be formed over a plurality of pixels 7. The opposite electrode **op** is formed not only in a display section 11 including pixels 7, but also over the entire surface of the transparent substrate 10.

[0006] With reference to Figs. 23 and 24(A) again, the other source-drain region of the second TFT 30 is electrically connected to the common feed line **com** through a contact hole in the first insulating interlayer 51. An extension 39 of the common feed line **com** faces an extension 36 of the gate electrode 31 in the second TFT 30 separated by the first insulating interlayer 51 as a dielectric film to form a holding capacitor **cap**.

[0007] In the active matrix display device 1A, however, only the second insulating interlayer 52 is disposed between the opposite electrode **op** facing the pixel electrode 41 and the data line **sig** on the same transparent substrate 10, unlike liquid crystal active matrix display devices; hence, a large capacitance is formed in the data line **sig** and the data line driving circuit 3 is heavily loaded.

[0008] Accordingly, as shown in Figs. 22, 23, 25(A), 25(B), and 25(C), the present inventors propose a reduction in parasitic capacitance in the data line **sig** by providing a thick insulating film (a bank layer **bank**; the region shaded with lines slanting downward to the left at a wide pitch) between the opposite electrode **op** and the data line **sig**. Furthermore, the present inventors propose that the region for forming the organic semiconductive film 43 be surrounded with the insulating film (bank layer **bank**) to contain any solution discharged from an ink-jet head and to prevent bleeding of the solution towards the sides during formation of the organic semiconductive film 43.

[0009] When the entire bank layer **bank** is formed of a thick inorganic material in adoption of such a configuration, a problem of a prolonged film forming time arises. When the thick inorganic film is patterned, the

pixel electrode 41 may be damaged due to overetching. On the other hand, when the bank layer bank is formed of an organic material, such as a resist, the organic semiconductor film 43 may deteriorate at the boundary between the organic semiconductor film 43 and the bank layer bank by the effects of the solvent components contained in the organic material in the bank layer bank.

[0010] Since formation of a thick bank layer bank causes formation of a large step difference bb, the opposite electrode op formed above the bank layer bank readily breaks on the step difference bb. Such breakage of the opposite electrode op due to the step difference bb causes insulation of the opposite electrode op from the neighboring opposite electrodes op to form point or linear defects in the display. When the opposite electrode op breaks along the outer periphery of the bank layer bank which covers the surfaces of the data line driving circuit 3 and the scanning line driving circuit 4, the opposite electrode op in the display section 11 is completely insulated from a terminal 12 and thus no image is displayed.

[0011] Accordingly, it is an object of the present invention in view of the above problems to provide an active matrix display device, without damage of thin film luminescent devices, having a thick insulating film satisfactorily formed around an organic semiconductor film in the thin film luminescent devices.

[0012] It is another object of the present invention to provide an active matrix display device without breakage of an opposite electrode formed on a thick insulating film which is formed around an organic semiconductor film to reduce parasitic capacitance.

Disclosure of Invention

[0013] The present invention for solving the above-mentioned problems is characterized by an active matrix display device comprising a display region including a plurality of scanning lines on a substrate, a plurality of data lines extending in the direction perpendicular to the direction of the scanning lines, and a plurality of pixels arranged in a matrix delimited by the data lines and the scanning lines; each of the pixels being provided with a thin film luminescent device having a conduction control circuit containing a thin film transistor for supplying a scanning signal to a gate electrode through one of the scanning lines, a pixel electrode, an organic semiconductor film deposited above the pixel electrode, and an opposite electrode deposited above the organic semiconductor film; the thin film luminescent device emitting light based on an image signal supplied from the data line through the conduction control circuit; wherein the region for forming the organic semiconductor film is divided by an insulating film which is thicker than the organic semiconductor film; and the insulating film comprises a lower insulating layer which is formed of an inorganic material and is thicker than the

organic semiconductor film, and an upper insulating layer which is deposited on the lower insulating layer and is formed of an organic material.

[0014] In the present invention, the data line will form large parasitic capacitance if the opposite electrode is formed on the entire surface of the display section to face the data line; however, a thick insulating film is provided between the data line and the opposite electrode in the present invention to prevent formation of the parasitic capacitance in the data line. As a result, a load on the data line driving circuit is reduced, and low energy consumption and high-speed display operation are achieved. If the thick insulating film is formed of only an inorganic material, a long film deposition time is required, resulting in low productivity. In the present invention, only the lower insulating layer in contact with the organic semiconductor film of the thin film luminescent device is formed of an inorganic material, and an upper insulating layer composed of an organic material such as a resist is formed thereon. Since the upper insulating layer composed of an organic material facilitates formation of a thick film and so results in improved productivity. The upper insulating layer does not come into contact with the organic semiconductor film, but the lower insulating layer composed of an inorganic material does come into contact with the organic semiconductor film; hence, the organic semiconductor film is protected from deterioration affected by the upper insulating layer. Accordingly, the thin film luminescent device does not have any decreased luminescent efficiency or reliability.

[0015] It is preferable in the present invention that the upper insulating layer be deposited in an inner region of the lower insulating layer so as to have a width narrower than that of the upper insulating layer. Such a two-step configuration prevents contact of the upper insulating layer composed of an organic material with the organic semiconductor film; hence deterioration of the organic semiconductor film can be more securely prevented.

[0016] In such a two-step configuration, both the lower insulating layer and the upper insulating layer may be formed of inorganic materials. Another aspect of the present invention is an active matrix display device comprising a display region including a plurality of scanning lines on a substrate, a plurality of data lines extending in the direction perpendicular to the direction of the scanning lines, and a plurality of pixels arranged in a matrix delimited by the data lines and the scanning lines; each of the pixels being provided with a thin film luminescent device having a conduction control circuit containing a thin film transistor for supplying a scanning signal to a gate electrode through one of the scanning lines, a pixel electrode, an organic semiconductor film deposited above the pixel electrode, and an opposite electrode deposited above the organic semiconductor film; the thin film luminescent device emitting light based on an image signal supplied from the data line through the conduction control circuit; wherein the region for form-

ing the organic semiconductive film is divided by an insulating film which is thicker than the organic semiconductive film; and the insulating film comprises a lower insulating layer composed of an inorganic material, and an upper insulating layer, composed of an inorganic material, so as to have a width which is narrower than that of the lower insulating layer.

[0017] In such a configuration, after films composed of inorganic materials, constituting a lower insulating layer and an upper insulating layer, are formed, the upper insulating layer is patterned. Since the lower insulating layer functions as an etching stopper, the pixel electrodes will not be damaged by slight overetching. After the patterning, the lower insulating layer is patterned. Since only one layer of the lower insulating layer is etched, the etching is readily controlled so that overetching, which would damage the pixel electrodes, does not occur.

[0018] It is preferable in the present invention that the conduction control circuit be provided with a first TFT for supplying the scanning signal to the gate electrode and a second TFT of which the gate electrode is connected to the data line through the first TFT, and that the second TFT and the thin film luminescent device be connected in series between a common feed line formed in addition to the data line and the scanning line for supplying a drive current and the opposite electrode. Although the conduction control circuit can be composed of a TFT and a holding capacitor, the conduction control circuit of each pixel is preferably composed of two TFTs and two holding capacitors for improving display quality.

[0019] It is preferable in the present invention that the insulating film be used as a bank layer which prevents bleeding of a discharged solution when the organic semiconductive film is formed by an ink-jet process in a region delimited by the insulating film. The insulating film preferably has a thickness of 1 μm or more.

[0020] It is preferable in the present invention that a region overlapping the area for forming the conduction control circuit in the region for forming the pixel electrode be covered with the insulating film. That is, it is preferable that within the region for forming the pixel electrode, the thick insulating film be opened only at the flat section not having the conduction control circuit and the organic semiconductive film be formed only at the interior thereof. Such a configuration can prevent display irregularities due to an irregular thickness of the organic semiconductive film. A thinner section of the organic semiconductive film causes a concentration of the driving current of the thin film luminescent device and decreased reliability; however, this configuration can prevent such a problem. If the organic semiconductive film emits light due to a driving current between a pixel electrode and the opposite electrode in the region overlapping the conduction control circuit, the light is shaded by the conduction control circuit and does not contribute to display. The driving current not contributing

to display by the shading effect of the conduction control circuit is an unavailable current. In the present invention, the thick insulating film is formed at the section, in which such an unavailable current is expected, to prevent formation of the unavailable current. As a result, a current in the common feed line can be reduced. Thus, by reducing the width of the common feed line, a luminescent area can be increased, improving display characteristics, such as luminance and contrast.

[0021] In the present invention, the corners delimited by the insulating film may be rounded so that the organic semiconductive film has a rounded planar shape. The organic semiconductive film having such a shape avoids the concentration of the driving current at the corners, hence defects, such as insufficient voltage resistance, can be prevented at the corners.

[0022] When the organic semiconductive film having a striped pattern is formed, the lower insulating layer of the insulating film is formed so as to cover the area for forming the conduction control circuit in the region for forming the pixel electrode, the data line, the common feed line, and the scanning line, whereas the upper insulating layer is formed so as to form a striped pattern along the data line, and the organic semiconductive film is formed in the region delimited by the striped pattern of the upper insulating layer by, for example, an ink-jet process.

[0023] In such a configuration, the conduction control circuit is covered with the lower insulating layer so that only the organic semiconductive film formed at the flat section of the pixel electrode contributes to luminescence. That is, the thin film luminescent device is formed only at the flat section of the pixel electrode. Thus, the resulting organic semiconductive film has a constant thickness and does not display irregularities. Since the lower insulating layer prevents a driving current in the section not contributing to display, an unavailable current in the common feed line can be prevented. In such a configuration, the section in which the lower insulating layer overlaps the upper insulating layer can be used as a bank layer for preventing bleeding of a discharged solution when the organic semiconductive film is formed by an ink-jet process. When the insulating film is used as a bank layer, the overlapping section of the lower insulating layer and the upper insulating layer preferably has a thickness of 1 μm or more.

[0024] It is preferable in the present invention that the insulating film have a first discontinuities portion so that opposite electrodes of adjacent pixels are connected to each other at flat sections formed by the first discontinuities portion. The thick insulating film in the present invention may form a large step which causes breakage of the opposite electrode formed thereon; however, the first discontinuities portion formed at predetermined positions of the thick insulating film are planarized. Since the opposite electrodes of individual regions are electrically connected to each other at the flat sections corresponding to the first discontinuities portion, the

opposite electrodes are protected from breakage even if breakage occurs at the step due to the insulating film. Since breakage of the opposite electrode formed above the insulating film does not occur when a thick insulating film is formed around the organic semiconductive film to suppress the parasitic capacitance, display quality and reliability of the active matrix display device can be improved.

[0025] When the insulating film is formed along the data line and the scanning line so as to surround the region for forming the organic semiconductive film, the first discontinuities portion are preferably formed between the adjacent pixels in the direction of the extending data line, between the adjacent pixels in the direction of the extending scanning line, or between the adjacent pixels in these directions.

[0026] When the insulating film extends in a striped pattern along the data line, the first discontinuity may be formed on at least one end of the extending direction.

[0027] It is preferable in the present invention that the periphery of the display section be provided with a data data lines, and a scanning line driving circuit for supplying scanning signals through the scanning lines, that the insulating film be also formed above the scanning line driving circuit and the data line driving circuit, and that the insulating film have a second discontinuity at a position between the region for forming the scanning line driving circuit and the region for forming the data line driving circuit so that the opposite electrodes at the display section and at the peripheral section of the substrate are connected through the flat section. Even if breakage of the opposite electrodes occurs along the periphery of the insulating film which covers the data line driving circuit and the scanning line driving circuit, the opposite electrode at the display section is connected to the opposite electrode at the periphery of the substrate via the flat section, and thus electrical connection between these opposite electrodes can be ensured.

[0028] In the discontinuity of the present invention, both the lower insulating layer and the upper insulating layer may have the discontinuity, or only the upper insulating layer between the upper insulating layer and the lower insulating layer may have the discontinuity.

Brief Description of the Drawings

[0029]

Fig. 1 is a schematic block diagram of an overall layout of an active matrix display device in accordance with a first embodiment of the present invention.

Fig. 2 is a plan view of a pixel taken from the active matrix display device shown in Fig. 1.

Figs. 3(A), 3(B) and 3(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 2.

Figs. 4(A), 4(B) and 4(C) are cross-sectional views

of active matrix display devices in accordance with a second embodiment and a third embodiment of the present invention at positions corresponding to line A-A', B-B', and C-C', respectively, in Fig. 2.

Fig. 5 is a plan view of a pixel taken from an active matrix display device in accordance with a fourth embodiment of the present invention.

Figs. 6(A), 6(B) and 6(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 5.

Fig. 7 is a schematic block diagram of an overall layout of an active matrix display device in accordance with a fifth embodiment of the present invention.

Fig. 8 is a plan view of a pixel taken from the active matrix display device shown in Fig. 7.

Figs. 9(A), 9(B) and 9(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 8.

Fig. 10 is a schematic block diagram of an overall layout of an active matrix display device in accordance with a first modification of the fifth embodiment of the present invention.

Fig. 11 is a plan view of a pixel taken from the active matrix display device shown in Fig. 10.

Figs. 12(A), 12(B) and 12(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 11.

Fig. 13 is a schematic block diagram of an overall layout of an active matrix display device in accordance with a second modification of the fifth embodiment of the present invention.

Fig. 14 is a plan view of a pixel taken from the active matrix display device shown in Fig. 13.

Figs. 15(A), 15(B) and 15(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 14.

Fig. 16 is a schematic block diagram of an overall layout of an active matrix display device in accordance with a third modification of the fifth embodiment of the present invention.

Fig. 17 is a plan view of a pixel taken from the active matrix display device shown in Fig. 16.

Figs. 18(A), 18(B) and 18(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 17.

Fig. 19 is a schematic block diagram of an overall layout of an active matrix display device in accordance with a sixth embodiment of the present invention.

Fig. 20 is a plan view of a pixel taken from the active matrix display device shown in Fig. 19.

Figs. 21(A), 21(B) and 21(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 20.

Fig. 22 is a schematic block diagram of an overall layout of a conventional active matrix display device or an active matrix display device in accordance

with a comparative embodiment of the present invention.

Fig. 23 is a plan view of a pixel taken from the active matrix display device shown in Fig. 22.

Figs. 24(A), 24(B) and 24(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 23.

Figs. 25(A), 25(B) and 25(C) are cross-sectional views of an active matrix display device in accordance with a comparative embodiment at positions corresponding to line A-A', B-B', and C-C', respectively, in Fig. 23.

[Reference Numerals]

[0030]

1	active matrix display device
2	display section
3	data line driving circuit
4	scanning line driving circuit
7	pixel
10	transparent substrate
12	terminal
20	first TFT
21	gate electrode of first TFT
30	second TFT
31	gate electrode of second TFT
40	luminescent device
41	pixel electrode
43	organic semiconductive material
61	lower insulating layer
62	upper insulating layer
bank	bank layer (insulating film)
cap	holding capacitor
com	common feed line
gate	scanning line
op	opposite electrode
off	discontinuity of bank layer
sig	data line

Best Mode for Carrying out the Invention

[0031] Embodiments of the present invention will now be described with reference to the drawings. Parts having the same functions as in Figs. 22 and 25 are referred to the same numerals.

[First Embodiment]

(Overall Configuration)

[0032] Fig. 1 is a schematic block diagram of an overall layout of an active matrix display device in accordance with the present invention. Fig. 2 is a plan view of one of the pixels extracted included therein. Figs. 3(A), 3(B) and 3(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 2.

[0033] In the active matrix display device 1 shown in Fig. 1, the central portion of a transparent substrate 10 as a base is used as a display section 11. Within the peripheral section of the transparent substrate 10, a data line driving circuit 3 for outputting image signals is provided on the ends of data lines sig, whereas a scanning line driving circuit 4 for outputting scanning signals is provided on the ends of scanning lines gate. In these driving circuits 3 and 4, an n-TFT and a p-TFT form a complementary TFT, and many complementary TFTs form a shift resistor circuit, a level shifter circuit, and an analog switch circuit. In the display section 11, like in an active matrix substrate of an active matrix liquid crystal display device, a plurality of scanning lines gate, a plurality of data lines sig extending perpendicular to the extending direction of the scanning lines gate, and a plurality of pixels 7 formed in a matrix by the data lines sig and the scanning lines gate are provided on the transparent substrate 10.

[0034] Each pixel 7 is provided with a conduction control circuit 50 for supplying scanning signals through a scanning line gate, and a thin film luminescent device 40 emitting light on the basis of image signals supplied from a data line sig through the conduction control circuit 50. In this embodiment, the conduction control circuit 50 includes a first TFT 20 for supplying a scanning signal to a gate electrode through a scanning line gate, a holding capacitor cap for holding an image signal supplied from a data line sig through the first TFT 20, and a second TFT 30 for supplying the image signal held in the holding capacitor cap to the gate electrode. The second TFT 30 and the thin film luminescent device 40 are connected in series between an opposite electrode op and a common feed line com. The holding capacitor cap may be formed between the opposite electrode op and the scanning line gate, in addition to between the opposite electrode op and the common feed line com.

[0035] As shown in Figs. 2, 3(A), and 3(B), in each pixel of the active matrix display device 1 having such a configuration, the first TFT 20 and the second TFT 30 are formed using islands of semiconductive films (silicon films).

[0036] In the first TFT 20, a gate electrode 21 is formed as a part of the scanning line gate. In the first TFT 20, one of the source and drain regions is electrically connected to the data line sig via a contact hole in a first insulating film 51, whereas the other is electrically connected to a drain electrode 22. The drain electrode 22 extends towards the region of the second TFT 30, and the extended section is electrically connected to a gate electrode 31 of the second TFT 30 via a contact hole in the first insulating film 51.

[0037] One of the source and drain regions of the second TFT 30 is electrically connected to a relay electrode 35 simultaneously formed with the data line sig via a contact hole in the first insulating film 51, and the relay electrode 35 is electrically connected to a transparent pixel electrode 41 composed of an indium tin oxide

(ITO) film in the thin film luminescent device 40 via a contact hole in a second insulating film 52.

[0038] As shown in Figs. 2, 3(B), and 3(C), pixel electrodes 41 are independently formed in individual pixels 7. An organic semiconductive film 43 composed of polyphenylene vinylene (PPV) or the like and an opposite electrode **op** composed of a metal film such as lithium-containing aluminum or calcium are deposited above each pixel electrode 41, in that order, to form a thin film luminescent device 40. Although an organic semiconductive film 43 is formed on each pixel in this embodiment, a stripe organic semiconductive film 43 will be formed over a plurality of pixels 7 in some cases, as will be described below. The opposite electrode **op** is formed over the entire display section 11, other than the periphery of the region in which terminals 12 are formed. The terminals 12 include a terminal electrically connected to the opposite electrode **op** formed using a conduction (not shown in the drawing) which is simultaneously formed with the opposite electrode **op**.

[0039] The configuration of the thin film luminescent device 40 may be a configuration provided with a positive hole injection layer having an increased luminescent efficiency (hole injection efficiency), or a configuration provided with a positive hole injection layer and an electron injection layer.

[0040] With reference to Figs. 2 and 3(A) again, the other of the source and drain regions of the second TFT 30 is electrically connected to the common feed line **com** via a contact hole of the first insulating film 51. The extension 39 of the common feed line **com** faces the extension 36 of the gate electrode 31 separated by the first insulating film 51 as a dielectric film to form a holding capacitor **cap**. In place of the common feed line **com**, a capacitor line formed parallel to the scanning line **gate** may be used for the formation of the holding capacitor **cap**. Alternatively, the holding capacitor **cap** may be formed of the drain region of the first TFT 20 and the gate electrode 31 of the second TFT 30.

[0041] In such an active matrix display device 1, when the first TFT 20 turns on by selection of a scanning signal, an image signal from the data line **sig** is applied to the gate electrode 31 of the second TFT 30 via the first TFT 20 and simultaneously stored in the holding capacitor **cap** via the first TFT 20. When the second TFT 30 turns on, a voltage is applied between the opposite electrode **op** as a negative electrode and the pixel electrode 41 as a positive electrode. When the voltage exceeds the threshold voltage, a current (a driving current) flowing in the organic semiconductive film 43 steeply increases. Thus, the luminescent device 40 emits light as an electroluminescent device or an LED device. Light from the luminescent device 40 is reflected by the opposite electrode **op**, passes through the transparent pixel electrode 41, and emerges from the transparent substrate 10. Since the driving current for performing such luminescence flows in a current passage including the opposite electrode **op**, the organic

semiconductive film 43, the pixel electrode 41, the second TFT 30, and the common feed line **com**, the current stops when the second TFT 30 turns off. The holding capacitor **cap**, however, holds the gate electrode of the second TFT 30 at a potential corresponding to the image signal; hence, the second TFT 30 still turns on. Thus, a driving current continues to flow in the luminescent device 40 so that the pixel maintains a turned-on state. This state is held until the second TFT 30 turns off by accumulation of the next image data in the holding capacitor **cap**.

(Bank Layer Configuration)

[0042] In order to prevent formation of a large parasitic capacitance in the data line **sig** in such an active matrix display device 1 in this embodiment, as shown in Figs. 1, 2, 3(A), 3(B), and 3(C), an insulating film (a bank layer **bank**, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than the organic semiconductive film 41 is provided along the data line **sig** and the scanning line **gate**, and the opposite electrode **op** is formed above the bank layer **bank**. Since the second insulating film 52 and the thick bank layer **bank** are disposed between the data line **sig** and the opposite electrode **op**, the parasitic capacitance formed in the data line **sig** is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0043] The bank layer **bank** consists of a lower insulating layer 61 which is formed of an inorganic material such as a silicon oxide film or a silicon nitride film and is thicker than the organic semiconductive film 41, and an upper insulating layer 62 which is formed on the lower insulating layer 61 and is composed of an organic material such as a resist or a polyimide film. For example, the thicknesses of the organic semiconductive film 41, the lower insulating layer 61, and the upper insulating layer 62 are in ranges of 0.05 μm to 0.2 μm , 0.2 μm to 1.0 μm , and 1 μm to 2 μm , respectively.

[0044] In such a double-layer configuration, the upper insulating layer 62 is formed of a resist or a polyimide film which facilitates formation of a thick film; hence, only the lower insulating layer 61 can be formed of an inorganic material. Since the entire bank layer **bank** is not formed of an inorganic material, the formation of the inorganic film by, for example, a PECVD process does not require a long time. Thus, productivity of the active matrix display device 1 is increased.

[0045] Also, in such a double-layer configuration, the organic semiconductive film 41 comes into contact with the inorganic lower insulating layer 61, but not with the organic upper insulating layer 62. The organic semiconductive film 41 is, therefore, not damaged by the effects of the organic upper insulating layer 62, and the thin film luminescent device 40 does not have decreased luminescent efficiency nor decreased reliability.

[0046] As shown in Fig. 1, the bank layer **bank** is also formed in the peripheral region of the transparent substrate 10 (the exterior region of the display section 11); hence the data line driving circuit 3 and the scanning line driving circuit 4 are covered with the bank layer **bank**. The opposite electrode **op** must be formed at least in the display section 11, but is unnecessary in the driving circuit region. Since the opposite electrode **op** is generally formed by a mask sputtering process, an inaccurate alignment such as overlap of the opposite electrode **op** and the driving circuits may occur. In this embodiment, however, the bank layer **bank** is disposed between the lead layer of the driving circuits and the opposite electrode **op**; hence formation of parasitic capacitance in the driving circuits 3 and 4 is prevented even if the opposite electrode **op** overlaps the driving circuits. As a result, the load on the driving circuits 3 and 4 is reduced, consumption of electrical power is reduced, and high-speed display operation is achieved.

[0047] In this embodiment, the bank layer **bank** is also formed in the area, which overlaps the relay electrode 35 of the conduction control circuit 50, in the region for forming the pixel electrode 41. The organic semiconductive film 43 is, therefore, not formed in the area overlapping the relay electrode 35. Since the organic semiconductive film 43 is formed only at the flat section in the region for forming the pixel electrode 41, the resulting organic semiconductive film 43 has a constant thickness so that irregularities of display do not occur. If the organic semiconductive film 43 has a part having a lesser thickness, the driving current for the thin film luminescent device 40 is concentrated therein, resulting in decreased reliability of the thin film luminescent device 40. The uniform thickness in this embodiment does not cause such a problem. If the bank layer **bank** is not provided in the region overlapping the relay electrode 35, the organic semiconductive film 43 emits light by a driving current between the relay electrode 35 and the opposite electrode **op**; however, the relay electrode 35 and the opposite electrode **op** inhibit emission of the light to the exterior, and the light does not contribute to display. The driving current flowing in the section which does not contribute to display is an unavailable current in view of the display. In this embodiment, the bank layer **bank** is formed at the position in which an unavailable current will flow so as to prevent an unavailable current flowing in the common feed line **com**. Thus, the width of the common feed line **com** can be reduced. As a result, the luminescent area, which contributes to improved display performance, such as luminance and contrast, can be increased.

[0048] When the bank layer **bank** is formed of a black resist, the bank layer **bank** functions as a black matrix which improves the quality of display, such as contrast. In the active matrix display device 1 of this embodiment, the opposite electrode **op** is formed on the entire pixel 7 at the front face of the transparent substrate 10; hence light reflected by the opposite electrode **op** causes

decreased contrast. When the bank layer **bank** for preventing the formation of the parasitic capacitance is formed of a black resist, the bank layer **bank** also functions as a black matrix which shades the light reflected by the opposite electrode **op** and contributes to high contrast.

(Method for Making Active Matrix Display Device)

[0049] Since the resulting bank layer **bank** surrounds the region for forming the organic semiconductive film 43, the layer can prevent bleeding of a discharged solution outside when the organic semiconductive film 43 is formed by discharging a liquid material (discharging solution) through an ink-jet head in the production process of the active matrix display device. In the following method for making the active matrix display device 1, the steps for making the first TFT 20 and the second TFT 30 on the transparent substrate 10 are substantially the same as the steps for making the active matrix substrate of the active matrix liquid crystal display device; hence only the outline thereof will be briefly described with reference to Figs. 3(A), 3(B), and 3(C).

[0050] First, an underlying protective film (not shown in the drawing) composed of a silicon oxide film with a thickness of approximately 2,000 to 5,000 angstroms is formed, if necessary, on a transparent substrate 10 by a plasma enhanced CVD using tetraethoxysilane (TEOS) and gaseous oxygen as formation gases. A semiconductive film composed of an amorphous silicon film with a thickness of approximately 300 to 700 angstroms is formed on the underlying protective film by a plasma enhanced CVD. The amorphous silicon semiconductive film is subjected to a crystallization step, such as a laser annealing step or a solid phase deposition step so that the semiconductive film is crystallized to form a polysilicon film.

[0051] The semiconductive film is patterned to form islands of semiconductive films, and then a gate insulating film 57 composed of a silicon oxide or silicon nitride film with a thickness of approximately 600 to 1,500 angstroms is formed thereon by a plasma enhanced CVD using tetraethoxysilane (TEOS), gaseous oxygen and the like as formation gases.

[0052] Next, a conductive film composed of a metal film, such as aluminum, tantalum, molybdenum, titanium, or tungsten, is formed by a sputtering process, and is patterned to form gate electrodes 21 and 31 and an extension 36 of the gate electrode 31 (a gate electrode forming step). This step also forms a scanning line gate.

[0053] In such a state, a high concentration of phosphorus ions are implanted to form source and drain regions by self-alignment with respect to the gate electrodes 21 and 31. The section which is not doped with the impurity functions as a channel region.

[0054] After forming a first insulating interlayer 51 and then forming contact holes, a data line **slg**, a drain elec-

trode 22, a common feed line **com**, an extension 39 of the common feed line **com**, and a relay electrode 35 are formed. As a result, a first TFT 20, a second TFT 30, and a holding capacitor **cap** are formed.

[0055] Next, a second insulating interlayer 52 is formed and a contact hole is formed at the position corresponding to the relay electrode 35 of the insulating interlayer. An ITO film is formed on the entire second insulating interlayer 52 and is patterned, and then a pixel electrode 41 which is electrically connected to the source and drain regions of the second TFT 30 via the contact hole is formed in each pixel 7.

[0056] An inorganic film (for forming a lower insulating layer 61) is formed on the front face of the second insulating film 52 by a PECVD process, and then a resist (upper insulating layer 62) is formed along the scanning line **gate** and the data line **sig**. The inorganic film is patterned through the resist as a mask to form a lower insulating layer 61. Since the lower insulating layer 61 is thin, overetching does not occur when the lower insulating layer 61 is formed by such a patterning process. Thus, the pixel electrode 41 is not damaged.

[0057] After such an etching step, the inorganic film forms the lower insulating layer 61 along the scanning line **gate** and the data line **sig**. As a result, a double-layered bank layer **bank** including the lower insulating layer 61 and the upper insulating layer 62 is formed. In this step, the resist section remaining along the data line **sig** has a large width so as to cover the common feed line **com**. Thus, a region for forming the organic semiconductive film 43 in the luminescent device 40 is surrounded with the bank layer **bank**.

[0058] Organic semiconductive films 43 corresponding to R, G, and B are formed in regions in a matrix delimited by the bank layer **bank** by an ink-jet process. A liquid material (a precursor or a discharging solution) for forming the organic semiconductive film 43 is discharged in the inner region of the bank layer **bank** through an ink-jet head and fixed in the inner region of the bank layer **bank** to form the organic semiconductive film 43. Since the upper insulating layer 62 of the bank layer **bank** is composed of a resist or a polyimide film, it has water-repellent properties. In contrast, the precursor of the organic semiconductive film 43 contains a hydrophilic solution; hence, the region for forming the organic semiconductive film 43 is surely defined by the bank layer **bank**. Since the solution does not bleed out of the adjacent pixels 7, the organic semiconductive film 43 can be formed only in the predetermined region.

[0059] In this step, since the precursor discharged from the ink-jet head forms a convex surface with a thickness of approximately 2 μm to 4 μm due to surface tension, the bank layer must have a thickness of approximately 1 μm to 3 μm . Although the precursor discharged from the ink-jet head comes into contact with the upper insulating layer 62 in this state, the solvent in the precursor is removed by heat treatment at 100°C to 150°C. Thus, the thickness of the organic semiconduc-

tive film 43 in the inner region of the bank layer **bank** is fixed in a range of approximately 0.05 μm to 0.2 μm . The organic semiconductive film 43 no longer is in contact with the upper insulating layer 62.

[0060] When the bank layer **bank** has a height of 1 μm or more, the bank layer **bank** sufficiently functions as a barrier even if the bank layer **bank** does not have water-repellent properties. Such a thick bank layer **bank** can define the region for forming the organic semiconductive film 43 when the film is formed by a coating process in place of the ink-jet process.

[0061] Next, an opposite electrode **op** is formed on substantially the entire transparent substrate 10.

[0062] According to the method, organic semiconductive films 43 can be formed at predetermined positions corresponding to R, G, and B by an ink-jet process; hence a full color active matrix display device 1 can be made with high productivity.

[0063] Although TFTs are also formed in the data line driving circuit 3 and the scanning line driving circuit 4 shown in Fig. 1, these TFTs can be formed by completely or partly employing the above steps for forming the TFT in the pixel 7. Thus, the TFTs in the driving circuits are also formed in the same interlayer in which TFTs for pixels 7 are formed. In addition to the first TFT 20 and the second TFT 30, combinations of an n-type and an n-type, of a p-type and a p-type, and of an n-type and a p-type are allowable. Since all the combinations of TFTs can be produced by any well-known method, description thereof will be omitted.

[Second Embodiment]

[0064] Figs. 4(A), 4(B) and 4(C) are cross-sectional views of an active matrix display device in accordance with this embodiment at positions corresponding to line A-A', B-B', and C-C', respectively, in Fig. 2. This embodiment has a basic configuration which is substantially the same as that of the first embodiment; hence, the same symbols are assigned for the same parts, without detailed description thereof. Since the region for forming the bank layer **bank** in the active matrix display device of this embodiment is the same as that in the first embodiment, Figs. 1 and 2 are also referred to in the following description.

[0065] In order to prevent formation of a large parasitic capacitance in a data line **sig**, also, in this embodiment, as shown in Figs. 1, 2, 4(A), 4(B), and 4(C), an insulating film (a bank layer **bank**, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 41 is provided along the data line **sig** and a scanning line **gate**, and an opposite electrode **op** is formed above the bank layer **bank**.

[0066] As in the first embodiment, the bank layer **bank** consists of an inorganic lower insulating layer 61 such as a silicon oxide or silicon nitride film which is thicker than the organic semiconductive film 41, and an upper

organic insulating film 62 such as a resist or a polyimide film formed on the lower insulating layer 61.

[0067] In this embodiment, as shown in Figs. 4(A), 4(B) and 4(C), the upper organic insulating film 62 has a smaller width than that of the lower inorganic insulating film 61 and is formed on the inner region of the lower insulating layer 61. For example, the overlapping width of the upper insulating layer 62 and the pixel electrode 41 is in a range of 1 μm to 3 μm , and a gap between an edge of the lower insulating layer 61 and the corresponding edge of the upper insulating layer 62 is in a range of 1 μm to 5 μm . Thus, the bank layer bank has a double-layered configuration in which the underlying insulating film 61 and the upper insulating layer 62 having different widths are deposited. The upper insulating layer 62 is formed of a resist or a polyimide film, which facilitates formation of a thick film, in such a double-layered configuration, and only the lower insulating layer 61 is composed of an inorganic material. The process, such as a PECVD process, for forming the inorganic film does not require a long deposition time, unlike the process for forming a thick bank layer bank which is entirely composed of an inorganic material. Thus, the active matrix display device 1 can be manufactured with high productivity. In such a double-layered configuration, the organic semiconductive film 41 comes into contact with the lower insulating layer 61, but not with the upper insulating layer 62. Furthermore, the upper insulating layer 62 is formed on the inner portion of the lower insulating layer 61 to avoid the contact of the organic semiconductive film 43 with the upper insulating layer 62. Thus, the upper organic insulating film 62 does not cause deterioration of the organic semiconductive film 41 which would result in decreased luminescent efficiency and decreased reliability of the thin film luminescent device 40.

[0068] The other configurations are the same as those in the first embodiment. Each pixel 7 is surrounded with the bank layer bank. Organic semiconductive films 43 can be formed in predetermined positions corresponding to R, G, and B by an ink-jet process; hence, a full color active matrix display device 1 can be manufactured with high productivity, as in the first embodiment.

[0069] In the formation of the bank layer bank having such a configuration, an inorganic film (for forming a lower insulating layer 61) is formed on the front face of the second insulating film 52 by a PECV process, the lower insulating layer 61 is formed along the scanning line gate and the data line sig, and then a resist used for the patterning is removed. Next, a resist or a polyimide film with a thickness which is smaller than that of the lower insulating layer 61 is formed thereon as the upper insulating layer 62. Since the lower insulating layer 61 is thin, overetching does not occur when the lower insulating layer 61 is formed by patterning. Thus, the pixel electrode 41 is not damaged.

[Third Embodiment]

[0070] An active matrix display device 1 in this embodiment has the same configuration as that in the second embodiment, but a material for the bank layer bank is different. Thus, the same symbols are assigned for the same parts, without detailed description thereof. Figs. 1, 2, and 4 are also referred to in the following description, as in the second embodiment.

[0071] In order to prevent formation of a large parasitic capacitance in a data line sig, as shown in Figs. 1, 2, 4(A), 4(B), and 4(C), an insulating film (a bank layer bank, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 41 is provided along the data line sig and a scanning line gate, and an opposite electrode op is formed above the bank layer bank.

[0072] The bank layer bank consists of an inorganic lower insulating layer 61 such as a silicon nitride film which is thicker than the organic semiconductive film 41, and an upper inorganic insulating film 62 such as a silicon oxide film formed on the lower insulating layer 61. Since the organic semiconductive film 43 does not come into contact with any other organic material in such a double-layered configuration, it will not be deteriorate by the effects of the other organic material. Thus, a decrease in luminescent efficiency and reliability does not occur in the thin film luminescent device 40.

[0073] The upper organic insulating film 62 has a smaller width than that of the lower inorganic insulating film 61 and is formed on the inner region of the lower insulating layer 61. Thus, the bank layer bank has a double-layered configuration in which the underlying insulating film 61 and the upper insulating layer 62 having different widths are deposited.

[0074] In the formation of the bank layer bank having such a configuration, inorganic films (a silicon nitride film and a silicon oxide film) for forming the lower insulating layer 61 and the upper insulating layer 62 are formed in that order, and the upper insulating layer 62 is patterned. Since the lower insulating layer 61 functions as an etching stopper, slight overetching will not damage the pixel electrode 41. After the patterning, the lower insulating layer 61 is patterned. Since a single layer of the lower insulating layer 61 is etched, the etching is readily controlled and overetching which would damage the pixel electrode 41 does not occur.

[0075] The other configurations are the same as those in the first and second embodiments. Each pixel 7 is, therefore, surrounded with the bank layer bank. Organic semiconductive films 43 can be formed in predetermined positions corresponding to R, G, and B by an ink-jet process; hence, a full color active matrix display device 1 can be manufactured with high productivity, as in the first embodiment.

[Modifications of First, Second, and Third Embodiments]

[0076] Since the bank layer **bank** is formed along the data line **sig** and the scanning line **gate** in the above embodiments, the bank layer **bank** delimits pixels 7 in a matrix. The bank layer **bank** may be formed along only the data line **sig**. Organic semiconductive film 43 having a striped pattern, corresponding to R, G, and B, can be formed in striped regions delimited by the bank layer **bank** by an ink-jet process; hence a full color active matrix display device 1 can be made with high productivity.

[0077] Although the corners delimited by the bank layer **bank** are edged in the above embodiments, it may be rounded so that the organic semiconductive film 43 has a rounded planar shape. The organic semiconductive film 43 having such a shape avoids the concentration of the driving current at the corners, hence defects, such as insufficient voltage resistance, can be prevented at the corners.

[Fourth Embodiment]

[0078] An active matrix display device 1 in this embodiment has a basic configuration like that in the first, second or third embodiment; hence, Fig. 1 is referred to for the description, and the same symbols are assigned for the same parts, without detailed description thereof.

[0079] Fig. 5 is a plan view of a pixel taken from an active matrix display device of this embodiment. Figs. 6(A), 6(B) and 6(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 5.

[0080] As described below, an upper insulating layer 62 partly overlaps a lower insulating layer 61 in this embodiment so that these films have different functions. As shown in Fig. 1, also, in this embodiment, a plurality of scanning lines **gate**, a plurality of data lines **sig** extending perpendicular to the extending direction of the scanning lines **gate**, a plurality of common feed lines **com** formed parallel to the data lines **sig**, and a plurality of pixels 7 formed in a matrix by the data lines **sig** and the scanning lines **gate** are provided.

[0081] In this embodiment, as shown in Figs. 5 and 6, a lower insulating layer 61 (a region shaded by double lines slanting down toward the left) is formed so as to cover an area overlapping the portion for forming a conduction control circuit 50 in the region for forming a pixel electrode 41; the data line **sig**; the common feed line **com**; and the scanning line **gate**. On the other hand, the upper insulating layer 62 (a region shaded by lines at a wide pitch and slanting down toward the left) is formed only on areas along the data lines **sig** in the region for forming the lower insulating layer 61 so as to form a striped pattern. Organic semiconductive films 43 are formed in the striped areas delimited by the upper insulating layer 62.

[0082] When the organic semiconductive films 43 hav-

ing the striped pattern are formed by an ink-jet process in such a configuration, the overlapping section of the lower insulating layer 61 and the upper insulating layer 62 is used as a bank layer **bank** to prevent bleeding of the discharged solution. In this embodiment, the overlapping section of the lower insulating layer 61 and the upper insulating layer 62 has a thickness of 1 μm or more.

[0083] Since the second insulating film 52 and the thick bank layer **bank** (the lower insulating layer 61 and the upper insulating layer 62) are disposed between the data lines **sig** and the opposite electrode **op** in such a configuration, parasitic capacitance forming in the data line **sig** is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0084] Although the striped organic semiconductive films 43 are formed, an area overlapping the portion for forming a conduction control circuit 50 in the region for forming the pixel electrode 41, and a scanning line **gate** are covered with the upper insulating layer 62. Thus, organic semiconductive film 43 formed only on the flat section in the pixel electrode 41 contributes to luminescence. In other words, the thin film luminescent device 40 is formed only in the flat section of the pixel electrode 41. Thus, the organic semiconductive film 43 has a constant thickness and does not cause irregularities of display and concentration of a driving current. Since the lower insulating layer 61 inhibits a current flow in the section which does not contribute to display, an unavailable current does not flow in the common feed line **com**.

[0085] When the underlying insulating film 61 is formed of an inorganic material such as a silicon oxide film or a silicon nitride film which is thicker than the organic semiconductive film 41 and when the upper insulating layer 62 is composed of an organic material such as a resist or a polyimide film, only the lower insulating layer 61 is composed of the inorganic material. Thus, the process, such as a PECVD process, for forming the inorganic film does not require a long deposition time, unlike the process for forming a thick bank layer **bank** which is entirely composed of an inorganic material. Thus, the active matrix display device 1 can be manufactured with high productivity. In such a double-layered configuration, the organic semiconductive film 41 comes into contact with the lower insulating layer 61, but not with the upper organic insulating film 62. Thus, the upper organic insulating film 62 does not cause deterioration of the organic semiconductive film 41 which results in decreased luminescent efficiency and decreased reliability of the thin film luminescent device 40.

[0086] When the lower insulating layer 61 is composed of an inorganic material such as a silicon nitride film which is thicker than the organic semiconductive film 41 and when the upper insulating layer 62 formed on the lower insulating layer 61 is composed of an inor-

ganic material such as a silicon oxide film, the organic semiconductive film 43 does not come into contact with an organic material and thus is not deteriorated by the effects of the organic material. Thus, a decrease in the luminescent efficiency and reliability does not occur in the thin film luminescent device 40. Since the underlying insulating film 61 with a smaller width is deposited on the inner region of the lower insulating layer 61, the lower insulating layer 61 functions as an etching stopper when the upper insulating layer 62 is patterned, as described in the third embodiment.

[Fifth Embodiment]

[0087] Fig. 7 is a schematic block diagram of an overall layout of an active matrix display device. Fig. 8 is a plan view of a pixel extracted therefrom. Figs. 9(A), 9(B) and 9(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 8. This embodiment has a basic configuration which is substantially the same as that of the first embodiment; hence, the same symbols are assigned for the same parts, without detailed description thereof.

[0088] Also, in this embodiment, an insulating film (a bank layer **bank**, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 41 is provided along the data line **sig** and a scanning line **gate**, and an opposite electrode **op** is formed above the bank layer **bank**. Since the second insulating film 52 and the thick bank layer **bank** are disposed between the data lines **sig** and the opposite electrode **op**, parasitic capacitance forming in the data line **sig** is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0089] The bank layer **bank** consists of a lower insulating layer 61 which is formed of an inorganic material such as a silicon oxide film or a silicon nitride film and is thicker than the organic semiconductive film 41, and an upper insulating layer 62 which is formed on the lower insulating layer 61 and is composed of an organic material such as a resist or a polyimide film. For example, the thicknesses of the organic semiconductive film 41, the lower insulating layer 61, and the upper insulating layer 62 are in ranges of 0.05 μm to 0.2 μm , 0.2 μm to 1.0 μm , and 1 μm to 2 μm , respectively. Thus, the organic semiconductive film 41 comes into contact with the inorganic lower insulating layer 61, but not with the organic upper insulating layer 62. The organic semiconductive film 41 is, therefore, not damaged by the effects of the organic upper insulating layer 62, and the thin film luminescent device 40, as in the first embodiment, does not have decreased luminescent efficiency nor decreased reliability.

[0090] In the active matrix display device 1 having such a configuration, the organic semiconductive film 41 is surrounded with the bank layer **bank**. Thus, the

opposite electrode **p** of each pixel 7 will be connected to the opposite electrode **p** of the adjacent pixel 7 over the bank layer **bank** as it stands. In this embodiment, discontinuities portion **off** (first discontinuities portion) are provided for both the lower insulating layer 61 and the upper insulating layer 62 of the bank layer **bank** along the data lines **sig** between adjacent pixels 7. Discontinuities portion **off** (first discontinuities portion) are also provided for both the lower insulating layer 61 and the upper insulating layer 62 of the bank layer **bank** along the scanning lines **gate** between adjacent pixels 7. Furthermore, discontinuities portion **off** (first discontinuities portion) are provided for both the lower insulating layer 61 and the upper insulating layer 62 of the bank layer **bank** at the ends of each data line **sig** and each scanning line **gate**.

[0091] Since the thick bank layer **bank** is not provided at each discontinuity **off**, the discontinuity **off** does not have a large step and is flat. Thus, the opposite electrode **op** formed at this section does not cause disconnection. The opposite electrodes **op** of adjacent pixels 7 are securely connected through the flat section not having a step of the bank layer **bank**. Accordingly, a thick insulating film (a bank layer **bank**) can be formed around a pixel 7 to suppress the parasitic capacitance, without disconnection of the opposite electrodes **op** formed on the thick insulating film (bank layer **bank**).

[0092] In the peripheral region of the transparent substrate 10 (the outer region of the display section 11), the data line driving circuit 3 and the scanning line driving circuit 4 are covered with the bank layer **bank** (the region is indicated by shading). Thus, the opposite electrode **op** provided above the region for forming these driving circuits is separated by the bank layer **bank** from the lead layer of these driving circuits. Since formation of the parasitic capacitance in the driving circuits can be prevented, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0093] Furthermore, a discontinuity **off** (second discontinuity) is provided for both the lower insulating layer 61 and the upper insulating layer 62 of the bank layer **bank** between the region for forming the scanning line driving circuit 4 and the region for the data line driving circuit 3. The opposite electrode **op** at the side of the display section 11 and the opposite electrode **op** at the peripheral side of the substrate are connected through the discontinuity **off** of the bank layer **bank**, and the discontinuity **off** is also a flat section not having a step. Since the opposite electrode **op** formed at the discontinuity **off** does not cause disconnection, the opposite electrodes **op** of the display section 11 and the opposite electrode **op** of the peripheral section of the substrate are securely connected through the discontinuity **off** of the bank layer **bank**. Thus, terminals 12 connected to the opposite electrode **op** of the peripheral section of the substrate are securely connected to the opposite electrode **op** of the display section 11.

[0094] Since the bank layer bank is also formed in an area in which the region for forming the pixel electrode 41 overlaps the relay electrode 35 of the conduction control circuit 50 in this embodiment, no unavailable current flows. Accordingly, the width of the common feed line com can be reduced.

[0095] In the production of the active matrix display device 1 having such a configuration, the bank layer bank is formed on the front face of the second insulating film 52 along the scanning lines gate and the data lines sig, as in the first embodiment. Discontinuities portion off are formed at predetermined positions of the bank layer bank. The bank layer bank formed along the data lines sig has a larger width so that it can cover the common feed line com. As a result, the region for forming the organic semiconductive film 43 in the thin film luminescent device 40 is surrounded with the bank layer bank.

[0096] Organic semiconductive films 43 corresponding to R, G, and B are formed in a region delimited as a matrix by the bank layer bank by an ink-jet process. A liquid material (a precursor) for forming the organic semiconductive film 43 is discharged into the inner region of the bank layer bank through an ink-jet head and is fixed in the inner region of the bank layer bank to form the organic semiconductive film 43. Since the upper insulating layer 62 of the bank layer bank is composed of a resist or a polyimide film, it has water-repellent properties. In contrast, the precursor of the organic semiconductive film 43 contains a hydrophilic solution; hence, the region for forming the organic semiconductive film 43 is surely defined by the bank layer bank, and the solution does not bleed out of the adjacent pixels 7. Since the discontinuities portion off provided in the bank layer bank which delimits the region for forming the organic semiconductive film 43 are narrow, the region for forming the organic semiconductive film 43 can be surely defined by the bank layer bank, and the solution does not bleed out into adjacent pixels 7. Accordingly, the organic semiconductive film 43 can be formed within a predetermined region.

[0097] Since the precursor discharged from the ink-jet head forms a convex surface with a thickness of approximately 2 μm to 4 μm by surface tension, the bank layer must have a thickness of approximately 1 μm to 3 μm . Although the precursor discharged from the ink-jet head comes into contact with the upper insulating layer 62 in this state, the solvent in the precursor is removed by heat treatment at 100°C to 150°C. Thus, the thickness of the organic semiconductive film 43 fixed in the inner region of the bank layer bank is in a range of approximately 0.05 μm to 0.2 μm . The organic semiconductive film 43 no longer is in contact with the upper insulating layer 62.

[0098] When the bank layer bank has a height of 1 μm or more, the bank layer bank sufficiently functions as a barrier even if the bank layer bank does not have water-repellent properties. Such a thick bank layer bank can

define the region for forming the organic semiconductive film 43 when the film is formed by a coating process in place of the ink-jet process.

[First Modification of Fifth Embodiment]

[0099] Fig. 10 is a schematic block diagram of an overall layout of an active matrix display device. Fig. 11 is a plan view of a pixel taken from the device. Figs. 12(A), 12(B) and 12(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 11. This embodiment has a basic configuration which is substantially the same as that of the first embodiment; hence, the same symbols are assigned for the same parts, without detailed description thereof.

[0100] Also, as shown in Figs. 10, 11, 12(A), 12(B), and 12(C), in the active matrix display device 1 of this embodiment, an insulating film (a bank layer bank, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 43 is provided along the data line sig and a scanning line gate, and an opposite electrode op is formed above the bank layer bank. Since the second insulating film 52 and the thick bank layer bank are disposed between the data lines sig and the opposite electrode op, parasitic capacitance forming in the data line sig is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0101] The bank layer bank consists of a lower insulating layer 61 which is formed of an inorganic material such as a silicon oxide film or a silicon nitride film and is thicker than the organic semiconductive film 43, and an upper insulating layer 62 which is formed on the lower insulating layer 61 and is composed of an organic material such as a resist or a polyimide film. Thus, the organic semiconductive film 43 comes into contact with the inorganic lower insulating layer 61, but not with the organic upper insulating layer 62. The organic semiconductive film 43 is, therefore, not damaged by the effects of the organic upper insulating layer 62, and the thin film luminescent device 40, as in the first embodiment, does not decreased luminescent efficiency nor decreased reliability.

[0102] In this embodiment, the bank layer bank is formed along the data line sig and the scanning line gate and each pixel 7 is surrounded with the bank layer bank. Organic semiconductive films 43 can be formed in predetermined positions corresponding to R, G, and B by an ink-jet process; hence, a full color active matrix display device 1 can be manufactured with high productivity.

[0103] Furthermore, discontinuities portion off (first discontinuities portion) are provided for the bank layer bank along the scanning line gate between adjacent pixels 7. Discontinuities portion off (first discontinuities portion) are also provided for the bank layer bank at the

ends of each data line **sig** and each scanning line **gate**. Furthermore, a discontinuity **off** (second discontinuity) is provided for the bank layer **bank** between the region for forming the scanning line driving circuit 4 and the region for the data line driving circuit 3. Thus, the opposite electrodes **op** are securely connected through the flat sections (discontinuities portion **off**) of the bank layer **bank** not having steps, and do not cause disconnection.

[Second Modification of Fifth Embodiment]

[0104] Fig. 13 is a schematic block diagram of an overall layout of an active matrix display device. Fig. 14 is a plan view of a pixel taken from the device. Figs. 15(A), 15(B) and 15(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 14. This embodiment has a basic configuration which is substantially the same as that of the first embodiment; hence, the same symbols are assigned for the same parts, without detailed description thereof.

[0105] Also, as shown in Figs. 13, 14, 15(A), 15(B), and 15(C), in the active matrix display device 1 of this embodiment, an insulating film (a bank layer **bank**, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 43 is provided along the data line **sig** and a scanning line **gate**, and an opposite electrode **op** is formed above the bank layer **bank**. Since the second insulating film 52 and the thick bank layer **bank** are disposed between the data lines **sig** and the opposite electrode **op**, parasitic capacitance forming in the data line **sig** is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0106] The bank layer **bank** consists of a lower insulating layer 61 which is formed of an inorganic material such as a silicon oxide film or a silicon nitride film and is thicker than the organic semiconductive film 43; and an upper insulating layer 62 which is formed on the lower insulating layer 61 and is composed of an organic material such as a resist or a polyimide film. Thus, the organic semiconductive film 43 comes into contact with the inorganic lower insulating layer 61, but not with the organic upper insulating layer 62. The organic semiconductive film 43 is, therefore, not damaged by the effects of the organic upper insulating layer 62, and the thin film luminescent device 40, as in the first embodiment, does not have decreased luminescent efficiency nor decreased reliability.

[0107] In this embodiment, the bank layer **bank** is formed along the data line **sig** and the scanning line **gate** and each pixel 7 is surrounded with the bank layer **bank**. Organic semiconductive films 43 can be formed in predetermined positions corresponding to R, G, and B by an ink-jet process; hence, a full color active matrix display device 1 can be manufactured with high produc-

tivity.

[0108] Furthermore, discontinuities portion **off** (first discontinuities portion) are provided for the bank layer **bank** along the data line **sig** between adjacent pixels 7. Discontinuities portion **off** (first discontinuities portion) are also provided for the bank layer **bank** at the ends of each data line **sig** and each scanning line **gate**. Furthermore, a discontinuity **off** (second discontinuity) is provided for the bank layer **bank** between the region for forming the scanning line driving circuit 4 and the region for the data line driving circuit 3. Thus the opposite electrodes **op** are securely connected through the flat sections (discontinuities portion **off**) of the bank layer **bank** not having steps, and do not cause disconnection.

[Third Modification of Fifth Embodiment]

[0109] Fig. 16 is a schematic block diagram of an overall layout of an active matrix display device. Fig. 17 is a plan view of a pixel taken from the device. Figs. 18(A), 18(B), and 18(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 17. This embodiment has a basic configuration which is substantially the same as that of the first and fifth embodiments; hence, the same symbols are assigned for the same parts, without detailed description thereof.

[0110] Also, as shown in Figs. 16, 17, 18(A), 18(B), and 18(C), in the active matrix display device 1 of this embodiment, an insulating film (a bank layer **bank**, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 43 is provided along the data line **sig** and a scanning line **gate**, and an opposite electrode **op** is formed above the bank layer **bank**. Since the second insulating film 52 and the thick bank layer **bank** are disposed between the data lines **sig** and the opposite electrode **op**, parasitic capacitance forming in the data line **sig** is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0111] The bank layer **bank** consists of a lower insulating layer 61 which is formed of an inorganic material such as a silicon oxide film or a silicon nitride film and is thicker than the organic semiconductive film 43, and an upper insulating layer 62 which is formed on the lower insulating layer 61 and is composed of an organic material such as a resist or a polyimide film.

[0112] In this embodiment, the bank layer **bank** is formed along the data line **sig** and the scanning line **gate** and each pixel 7 is surrounded with the bank layer **bank**. Organic semiconductive films 43 can be formed in predetermined positions corresponding to R, G, and B by an ink-jet process; hence, a full color active matrix display device 1 can be manufactured with high productivity.

[0113] Furthermore, discontinuities portion **off** (first discontinuities portion) are provided for the bank layer

bank along the data line **sig** between adjacent pixels 7. Discontinuities portion **off** (first discontinuities portion) are also provided for the bank layer **bank** at the ends of each data line **sig** and each scanning line **gate**. Furthermore, a discontinuity **off** (second discontinuity) is provided for the bank layer **bank** between the region for forming the scanning line driving circuit 4 and the region for the data line driving circuit 3.

[0114] In this embodiment, however, these discontinuities portion **off** are provided for only the upper insulating layer 62 between the lower insulating layer 61 (a region shaded by double slashes) and the upper insulating layer 62 (a region shaded by lines slanting down to the left) of the bank layer **bank**, and thus the lower insulating layer 61 is formed at the discontinuities portion **off**.

[0115] In such a configuration, only the thin lower insulating layer 61 is provided at the discontinuities portion **off**; hence, the opposite electrode **op** can be securely connected to each other through the discontinuities portion **off** without disconnection.

[0116] Although the lower insulating layer 61 is formed for the first and second discontinuities portion in this embodiment, the present invention is not limited to this embodiment. The lower insulating layer 61 may be formed for either the first discontinuities portion or the second discontinuity. The configuration of this embodiment in which the lower insulating layer 61 is formed at the discontinuities portion can be applied to the bank layer **bank** having a pattern described in any other embodiment.

[Sixth Embodiment]

[0117] Fig. 19 is a schematic block diagram of an overall layout of an active matrix display device. Fig. 20 is a plan view of a pixel taken from the device. Figs. 21(A), 21(B) and 21(C) are cross-sectional views taken from line A-A', B-B', and C-C', respectively, in Fig. 20. This embodiment has a basic configuration which is substantially the same as that of the first and fifth embodiments; hence, the same symbols are assigned for the same parts, without detailed description thereof.

[0118] Also, as shown in Figs. 19, 20, 21(A), 21(B), and 21(C), in the active matrix display device 1 of this embodiment, an insulating film (a bank layer **bank**, the region shaded with lines slanting downward to the left or double slanting lines at a wide pitch) which is thicker than an organic semiconductive film 43 is provided along the data line **sig** and a scanning line **gate**, and an opposite electrode **op** is formed above the bank layer **bank**. Since the second insulating film 52 and the thick bank layer **bank** are disposed between the data lines **sig** and the opposite electrode **op**, parasitic capacitance forming in the data line **sig** is significantly reduced. Thus, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0119] The bank layer **bank** consists of a lower insulating layer 61 which is formed of an inorganic material such as a silicon oxide film or a silicon nitride film and is thicker than the organic semiconductive film 43, and an upper insulating layer 62 which is formed on the lower insulating layer 61 and is composed of an organic material such as a resist or a polyimide film. Thus, the organic semiconductive film 43 comes into contact with the inorganic lower insulating layer 61, but not with the organic upper insulating layer 62. The organic semiconductive film 43 is, therefore, not damaged by the effects of the organic upper insulating layer 62, and the thin film luminescent device 40 does not have decreased luminescent efficiency nor decreased reliability.

[0120] Since the bank layer **bank** is formed along the data line **sig** in this embodiment, organic semiconductive film 43 having a striped pattern, corresponding to R, G, and B, can be formed in striped regions delimited by the bank layer **bank** by an ink-jet process; hence a full color active matrix display device 1 can be made with high productivity.

[0121] In addition, discontinuities portion **off** (first discontinuities portion) are provided for both the lower insulating layer 61 and the upper insulating layer 62 of the bank layer **bank** along the data lines **sig** at the ends of each data line **sig**. Thus, the opposite electrode **op** of each pixel 7 is connected to the opposite electrode **op** of the adjacent pixel 7 over the thick bank layer **bank** in the direction of the scanning line **gate**. In the direction of the data line **sig**, however, the opposite electrode **op** of each pixel 7 is connected to the opposite electrode **op** of the adjacent pixel 7 at the discontinuity **off** (the flat section not having a step due to the bank layer **bank**) at the ends of the data line **sig**. Since the opposite electrode **op** of each pixel 7 is connected to the opposite electrode **op** of the adjacent pixel 7 at the flat section not having a step due to the bank layer **bank**, the opposite electrode **op** of each pixel 7 does not cause disconnection.

[0122] In the peripheral region of the transparent substrate 10 (the outer region of the display section 11), the data line driving circuit 3 and the scanning line driving circuit 4 are covered with the bank layer **bank**. Thus, the opposite electrode **op** provided above the region for forming these driving circuits is separated by the bank layer **bank** from the lead layer of these driving circuits. Since formation of the parasitic capacitance in the driving circuits can be prevented, the load on the driving circuits 3 and 4 can be reduced, resulting in lower electrical power consumption and improved display operation.

[0123] Furthermore, the bank layer **bank**, which is formed above the scanning line driving circuit 4 and the data line driving circuit 3, has a discontinuity **off** (second discontinuity) between the region for forming the scanning line driving circuit 4 and the region for the data line driving circuit 3. The opposite electrodes are securely connected through the flat section not having a step due

to the bank layer bank (the discontinuity off) without disconnection.

[Other Embodiments]

[0124] As described in the third modification of the fifth embodiment, the configuration in which only the upper insulating layer 62 has discontinuities portion off of the bank layer bank may also be applied to the sixth embodiment.

[0125] As described in the fifth and sixth embodiments, the concept of provision of discontinuities portion off in the bank layer bank for avoiding disconnection of the opposite electrodes op is also applicable to a bank layer bank composed of an inorganic material, as described in the third embodiment.

Industrial Applicability

[0126] As described above, in the active matrix display device in accordance with the present invention, the insulating film which is formed so as to surround the region for forming the organic semiconductive film consists of a lower insulating layer which is composed of an inorganic material and is thicker than the organic semiconductive film, and an upper insulating layer which is formed thereon and is composed of an organic material. Since a thick insulating film is disposed between the data line and the opposite electrode, formation of parasitic capacitance in the data line can be prevented. Thus, the load on the data line driving circuit can be reduced, resulting in lower electrical power consumption and improved display operation. In the present invention, only the lower insulating layer in contact with the organic semiconductive film of the thin film luminescent device is formed of an inorganic material, and the upper insulating layer formed thereon is composed of an organic material which facilitates formation of a thick film. Thus, the process has high productivity. The upper insulating layer does not come into contact with the organic semiconductive film, but the lower insulating layer composed of an inorganic material does come into contact with the organic semiconductive film; hence, the organic semiconductive film is protected from deterioration caused by the upper insulating layer. Accordingly, the thin film luminescent device does not have decreased luminescent efficiency or reliability.

[0127] When the upper insulating layer is deposited in an inner region of the lower insulating layer so as to have a width narrower than that of the upper insulating layer, contact of the upper insulating layer composed of an organic material with the organic semiconductive film is more securely prevented.

[0128] In another embodiment of the present invention, the insulating film formed so as to surround the region for forming the organic semiconductive film consists of a lower insulating layer composed of an inorganic material and an upper insulating layer which is

formed on an inner region of the lower insulating layer and has a smaller width than that of the lower insulating layer. Thus, the thick insulating film disposed between the data line and the opposite electrode can prevent formation of parasitic capacitance in the data line. Thus, the load on the data line driving circuit can be reduced, resulting in lower electrical power consumption and improved display operation. When a lower inorganic insulating film and an upper inorganic film are formed and when the upper insulating layer is patterned, the lower insulating layer functions as an etching stopper. Thus, overetching which would damage the pixel electrode does not occur. After patterning of the upper insulating layer, only a single layer of the lower insulating layer is etched in the succeeding patterning. Thus, the etching is readily controlled and overetching which would damage the pixel electrode does not occur.

Claims

1. An active matrix display device comprising a display region including a plurality of scanning lines on a substrate, a plurality of data lines extending in the direction perpendicular to the direction of the scanning lines, and a plurality of pixels arranged in a matrix delimited by the data lines and the scanning lines; each of the pixels being provided with a thin film luminescent device having a conduction control circuit containing a thin film transistor for supplying a scanning signal to a gate electrode through one of the scanning lines, a pixel electrode, an organic semiconductive film deposited above the pixel electrode, and an opposite electrode deposited above the organic semiconductive film; the thin film luminescent device emitting light based on an image signal supplied from the data line through the conduction control circuit; wherein

the region for forming the organic semiconductive film is divided by an insulating film which is thicker than the organic semiconductive film; and

the insulating film comprises a lower insulating layer which is formed of an inorganic material and is thicker than the organic semiconductive film, and an upper insulating layer which is deposited on the lower insulating layer and is formed of an organic material.

2. An active matrix display device according to claim 1, wherein the upper insulating layer is deposited in an inner region of the lower insulating layer so as to have a width narrower than that of the lower insulating layer.
3. An active matrix display device comprising a display region including a plurality of scanning lines on a substrate, a plurality of data lines extending in the

direction perpendicular to the direction of the scanning lines, and a plurality of pixels arranged in a matrix delimited by the data lines and the scanning lines; each of the pixels being provided with a thin film luminescent device having a conduction control circuit containing a thin film transistor for supplying a scanning signal to a gate electrode through one of the scanning lines, a pixel electrode, an organic semiconductive film deposited above the pixel electrode, and an opposite electrode deposited above the organic semiconductive film; the thin film luminescent device emitting light based on an image signal supplied from the data line through the conduction control circuit; wherein

the region for forming the organic semiconductive film is divided by an insulating film which is thicker than the organic semiconductive film; and

the insulating film comprises a lower insulating layer composed of an inorganic material, and an upper insulating layer, composed of an inorganic material, so as to have a width which is narrower than that of the lower insulating layer.

4. An active matrix display device according to any one of claims 1 to 3, wherein the conduction control circuit is provided with a first TFT for supplying the scanning signal to the gate electrode and a second TFT of which the gate electrode is connected to the data line through the first TFT; and

the second TFT and the thin film luminescent device are connected in series between a common feed line formed in addition to the data line and the scanning line for supplying a drive current and the opposite electrode.

5. An active matrix display device according to any one of claims 1 to 4, wherein the insulating film is used as a bank layer which prevents bleeding of a discharged solution when the organic semiconductive film is formed by an ink-jet process in a region delimited by the insulating film.
6. An active matrix display device according to claim 5, wherein the insulating film has a thickness of 1 μm or more.
7. An active matrix display device according to any one of claims 1 to 6, wherein a region overlapping the area for forming the conduction control circuit in the region for forming the pixel electrode is covered with the insulating film.
8. An active matrix display device according to any one of claims 1 to 7, wherein the corners delimited by the insulating film are rounded.

9. An active matrix display device according to any one of claims 1 to 4, wherein the lower insulating layer of the insulating film is formed so as to cover the area for forming the conduction control circuit in the region for forming the pixel electrode, the data line, the common feed line, and the scanning line, whereas the upper insulating layer is formed so as to form a striped pattern along the data line; and

the organic semiconductive film is formed in the region delimited by the striped pattern of the upper insulating layer.

10. An active matrix display device according to claim 9, wherein the overlapping section in which the lower insulating layer overlaps the upper insulating layer is used as a bank layer for preventing bleeding of a discharged solution when the luminescent thin film is formed by an ink-jet process.

11. An active matrix display device according to claim 10, wherein the overlapping section of the lower insulating layer and the upper insulating layer has a thickness of 1 μm or more.

12. An active matrix display device according to any one of claims 1 to 11, wherein the insulating film has first discontinuities portion so that opposite electrodes of adjacent pixels are connected to each other at flat sections formed by the first discontinuities portion.

13. An active matrix display device according to claim 12, wherein the insulating film is formed along the data line and the scanning line so as to surround the region for forming the organic semiconductive film, and the first discontinuities portion are formed between the adjacent pixels in the direction of the extending data line and in the direction of the extending scanning line.

14. An active matrix display device according to claim 12, wherein the insulating film is formed along the data line and the scanning line so as to surround the region for forming the organic semiconductive film, and the first discontinuities portion are formed between the adjacent pixels in the direction of the extending scanning line.

15. An active matrix display device according to claim 12, wherein the insulating film is formed along the data line and the scanning line so as to surround the region for forming the organic semiconductive film, and the first discontinuities portion are formed between the adjacent pixels in the direction of the extending data line.

16. An active matrix display device according to claim

12, wherein the insulating film extends in a striped pattern along the data line, and the first discontinuity is formed on at least one end of the extending direction.

17. An active matrix display device according to claim 12, wherein the periphery of the display section is provided with a data line driving circuit for supplying data signals through the data lines, and a scanning line driving circuit for supplying scanning signals through the scanning lines, the insulating film is also formed above the scanning line driving circuit and the data line driving circuit, and the insulating film has a second discontinuity at a position between the region for forming the scanning line driving circuit and the region for forming the data line driving circuit so that the opposite electrodes at the display section and at the peripheral section of the substrate are connected through the flat section not having a step formed by the insulating film.
18. An active matrix display device according to any one of claims 12 to 17, wherein both the lower insulating layer and the upper insulating layer have the discontinuities portion.
19. An active matrix display device according to any one of claims 12 to 17, wherein only the upper insulating layer between the lower insulating layer and the upper insulating layer may have the discontinuities portion.

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20




Fig. 21




Fig. 22




Fig. 23




Fig. 24





Fig. 25



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP98/03699

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl.⁶ G09F9/30, H01L33/00, H05B33/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl.⁶ G09F9/30, 9/33, H01L33/00

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Jitsuyo Shinan Koho 1926-1995

Kokai Jitsuyo Shinan Koho 1971-1995

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP, 2-66867, A (Matsushita Electric Industrial Co., Ltd.), 6 March, 1990 (06. 03. 90) (Family: none)	1-19
A	JP, 52-64891, A (Westinghouse Electric Corp.), 28 May, 1977 (28. 05. 77) & US, 4042854, A & US, 4135959, A	1-19
A	JP, 9-161970, A (Stanley Electric Co., Ltd.), 20 June, 1997 (20. 06. 97) (Family: none)	1-19

☐ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reasons (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search
9 November, 1998 (09. 11. 98)Date of mailing of the international search report
17 November, 1998 (17. 11. 98)Name and mailing address of the ISA/
Japanese Patent Office

Authorized officer

Facsimile No.

Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)